

**ANALİZ SONUÇLARI**  
RESULTS OF ANALYSIS

<b>Analizler</b> <i>Tests</i>	<b>Birim</b> <i>Unit</i>	<b>Analiz Metodu</b> <i>Test Method</i>	<b>Orijinal Baz</b> <i>Original Basis</i>	<b>Kuru Baz</b> <i>Dry Basis</i>
<b>Toplam Nem</b> <i>Total Moisture</i>	%	TS ISO 589-B	13,86	-
<b>Uçucu Madde</b> <i>Volatile Matter</i>	%	ASTM D 7582	37,87	43,96
<b>Kül</b> <i>Ash</i>	%	ASTM D 7582	7,60	8,82
<b>Sabit Karbon</b> <i>Fixed Carbon</i>	%	ASTM D 7582	40,67	47,22
<b>Toplam Kükürt</b> <i>Total Sulphur</i>	%	ASTM D 4239	0,90	1,04
<b>Brüt Kalorifik Değer</b> <i>Gross Calorific Value</i>	kcal/kg	ASTM D 5865	5686	6601
<b>Net Kalorifik Değer</b> <i>Net Calorific Value</i>	kcal/kg	ISO 1928	5396	6353